

Application Serial No. 10/623,743
Amendment dated January 31, 2005
Reply to Office Action dated December 1, 2004

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1-9 (canceled)

10. (previously presented): A method for preparing a united flexible exothermic medium, said method comprising:

mixing an exothermic agent which generates heat in contact with air and a water-absorptive polymer to form a first mixture;

mixing the first mixture with an alcohol which is selected from the group consisting of ethanol, isopropyl alcohol, ethylene glycol, propylene glycol and glycerin to form a second mixture; and

subjecting the second mixture to pressure.

11. (previously presented): A method for preparing a heating element which has a united flexible exothermic medium, said method comprising:

mixing an exothermic agent which generates heat in contact with air and a water-absorptive polymer to form a first mixture;

mixing the first mixture with an alcohol which is selected from the group consisting of ethanol, isopropyl alcohol, ethylene glycol, propylene glycol and glycerin to form a second mixture; and

subjecting the second mixture to pressure.

12. (previously presented): The method according to claim 10 wherein said pressure is 100-8000 kg/cm².

Application Serial No. 10/623,743
Amendment dated January 31, 2005
Reply to Office Action dated December 1, 2004

13. (previously presented): The method according to claim 12 wherein said pressure is 840-8000 kg/cm².

14. (previously presented): The method according to claim 10 wherein a second polymer is added to said first mixture of said exothermic agent and said water-absorptive polymer.

15. (previously presented): The method according to claim 11 wherein said pressure is 100-8000 kg/cm².

16. (previously presented): The method according to claim 11 wherein said pressure is 840-8000 kg/cm².

17. (previously presented): The method according to claim 11 wherein a second polymer is added to said first mixture of said exothermic agent and said water-absorptive polymer.

18. (previously presented): The method according to claim 11 further including the step of molding said medium in the shape of a flat layer with two main surfaces, and disposing an adhesive layer on one said surface.